

Technical Data Sheet

ABSODAN Plus



Printing Date 22/03/2022
Version 2019-12-11

Product Description

Diatomaceous earth (moler) granulated, calcined

Typical chemical analysis (after drying at 110°C)

SiO ₂	71,0 %
Fe ₂ O ₃	8,4 %
Al ₂ O ₃	10,5 %
TiO ₂	1,4 %
CaO	2,5 %
K ₂ O + Na ₂ O	2,1 %
MgO	1,6 %
Other oxides	1,1 %

Loss on ignition (1025°C)	0,94 %
Specific weight	2,3 g/cm ³
pH (10% aqueous suspension)	5,5

Specification	Min.	Max.	Average
Bulk Density		555 g/l	537 g/l
Absorption capacity, water (Westinghouse w/w)	110 %		124 %
Absorption capacity, oil (Westinghouse w/w)	75 %		96 %
Particle size distribution (w/w)	Min.	Max.	Average
> 1,5 mm		8 %	1,6 %
1,0-1,5 mm			37 %
0,5-1,0 mm			50 %
0,3 - 0,5 mm			10 %
0,09 - 0,3 mm		4,1 %	2,1 %
< 0,09 mm		1 %	0,2 %

The indicated values are an average of 12 months of laboratory tests.